

L3 ANSWER 1 OF 1 WPIX COPYRIGHT 2008 THOMSON REUTERS on STN
 AN 1995-355376 [46] WPIX
 DNC C1995-155699 [46]
 DNN N1995-264392 [46]
 TI Aromatic poly:carbonate resin compsn., used as moulding material -
 comprising aromatic poly:carbonate resin, filler, hydroxyl gp(s).-containing
 polymer and polylactone.
 DC A23; V04; X12
 IN HASHIMOTO Y
 PA (TEIQ-C) TEIJIN KASEI LTD
 CYC 1
 PIA JP 07242808 A 19950919 (199546)* JA 4[0] <--
 ADT JP 07242808 A JP 1994-35598 19940307
 PRAI JP 1994-35598 19940307
 AN 1995-355376 [46] WPIX
 AB JP 07242808 A UPAB: 20050513
 Aromatic polycarbonate resin compsn. (I) comprises (1) 100 pts.weight aromatic polycarbonate compsn. composed of (A) 50-99.9 weight% aromatic polycarbonate resin (II), (B) 0.1-50 weight% filler (III) containing fibrous filler with L/D (L=length, D=dia.) 3 or more above 20 weight%; (2) (C) 0.05-30 pts.weight hydroxyl gp(s).-containing polymer(s) (IV); and (3) (D) 0.05-30 pts.weight polylactone(s) (V). Pref. (II) is bisphenol A polycarbonate (IIa), (III) is e.g. glass fibre, (IV) is bisphenol A phenoxy resin (IVa) and/or bisphenol A epoxy resin, and (V) is polycaprolactone (Va). (I) is prepared e.g. by blending (II), (III), (IV), (V) and conventional additive(s) (e.g. flame-retardant, stabiliser, lubricant, colourant etc.), kneading the mixture by kneader or twin-screw extruder, and pelletising the kneaded prod.
 USE - (I) is useful as engineering plastic, e.g. moulding material for preparation of external parts of electric instruments, precision instruments etc.
 ADVANTAGE - (I) is moulded in a short moulding time, and gives mouldings having good appearance, gloss and mechanical strength.